## 1. PRODUCT IDENTIFICATION

Description

EFFECT CHAMPAGNE GLAZE.

It belongs to the "GLITTER EFFECT" serie. Is a collection of bright glitter glazes

Compound of frit: CAS No. 65997-18-4.

Application

The glaze can be applied by brush, screen printing or spray. They can be used for decoration of white, red body or over glaze. In all cases, the coat applied must be thin enough so that the glitter effect appears. The ratio of powder and water is approximately 500-800 ml of water per 100 gr of powder and 250 ml of Monocol V. It can be used in single and double firing. The firing temperature is 980 ° C.

## 2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	ZnO <b>1-5</b>	$Cr_2O_3$	CaF <sub>2</sub>		
Na <sub>2</sub> O <b>1-5</b>	MnO	B <sub>2</sub> O <sub>3</sub> <b>5-10</b>	Bi <sub>2</sub> O <sub>3</sub>	Co-Cr-Al 1-5	
K <sub>2</sub> ○ 0.5-1	CdO	$V_2O_5$	P <sub>2</sub> O <sub>5</sub>	MEDIUM 0-0.5	
MgO	CoO	$MnO_2$	BeO	Pig.Ing 40-80	1
CaO <b>1-5</b>	NiO	SiO <sub>2</sub> <b>20-40</b>	CeO <sub>2</sub>	Fig.ilig 40-60	,
SrO	$Al_2O_3$ <b>1-5</b>	TiO <sub>2</sub>	CuO		
BaO	Fe <sub>2</sub> O <sub>3</sub>	$ZrO_2$	Pr <sub>2</sub> O <sub>3</sub>		
PbO	$Sb_2O_3$	$SnO_2$			

## **3 PHYSICAL-CHEMICAL PROPERTIES**

Aspect Yellow powder

Color(fired) Bright glitter Champagne

4. COLORIMETRY \* By Minolta ChromaControl (S)

L: 71 a: 2.8 b: 17.2

**5. DILATOMETRY** \* Data obtained with dilatometer BÄHR mod. DIL 801 L

(25-300)C° (50-300)C° (300-500)C° (500-600)C° Ta Transformation Ta Softening Melting point

C° C° >800 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) \* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ >25μ >40μ >70μ >120μ D50μ 93.5 53.2 21.7 1.4 0 26.1

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

