Description

EFFECT COPPER GLAZE.

It belongs to the "GLITTER EFFECT" serie. Is a collection of bright glitter glazes

Compound of frit: CAS No. 65997-18-4.

Application

The glaze can be applied by brush, screen printing or spray. They can be used for decoration of white, red body or over glaze. In all cases, the coat applied must be thin enough so that the glitter effect appears. The ratio of powder and water is approximately 500-800 ml of water per 100 gr of powder and 250 ml of Monocol V. It can be used in single and double firing. The firing temperature is 980 ° C.

2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	ZnO	Cr_2O_3	CaF ₂	
Na ₂ O	MnO	B_2O_3	Bi_2O_3	
K_2O	CdO	V_2O_5	P ₂ O ₅	
MgO	CoO	MnO_2	BeO	
CaO	NiO	SiO ₂	CeO ₂	
SrO	Al_2O_3	TiO ₂	CuO	
BaO	Fe_2O_3	ZrO_2	Pr ₂ O ₃	
PbO	Sb_2O_3	SnO_2		

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Brown powder

Color(fired) Bright glitter copper

4. COLORIMETRY * By Minolta ChromaControl (S)

L: 58.2 a: 29.8 b: 16.5

5. DILATOMETRY * Data obtained with dilatometer BÄHR mod. DIL 801 L

(25-300)C° (50-300)C° (300-500)C° (500-600)C° Ta Transformation Ta Softening Melting point

C° C° >800 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) * Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ >25μ >40μ >70μ >120μ D50μ 78.9 31.7 9.3 0 0 12.7

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

