

DATA SHEET

20670404 ESMALTE GRES O- 6004 AZUL POLVO

18/11/2025 v1.3

1. PRODUCT IDENTIFICATION

Description	BLUE GLAZE. It belongs to high temperature glazes, with high rutile content. The result can be opaque matte, or satin. The final effect can be different depending on firing temperature, coat of glaze and kind of biscuit. The result will vary depending on the used body, temperature, cycle and atmosphere. Compound of frit: CAS N°. 65997-18-4.
Application	They can be applied by brush, spraying or dipping in single- and double-fired. For one firing it's advisable the addition of Monocol V. Temperature range 1200°C - 1340°C, recommended temperature 1260°C. It is advisable to test at extreme temperatures.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	ZnO	Cr ₂ O ₃	CaF ₂		
Na ₂ O 1-5	MnO	B ₂ O ₃	Bi ₂ O ₃	Co3O4	1-5
K ₂ O 1-5	CdO	V ₂ O ₅	P ₂ O ₅	MEDIUM	0-0.5
MgO 0-0.5	CoO	MnO ₂	BeO	LOI	10-20
CaO 10-20	NiO	SiO ₂ 40-80	CeO ₂		
SrO	Al ₂ O ₃ 5-10	TiO ₂ 5-10	CuO		
BaO	Fe ₂ O ₃ 0-0.5	ZrO ₂ 0-0.5	Pr ₂ O ₃		
PbO	Sb ₂ O ₃	SnO ₂			

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	Grey powder
Color(fired)	Blue

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: 52.6	a: 3.3	b: -22.0
---------	--------	----------

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10⁻⁷ C⁻¹

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
72.6	73.9	83.2	102.6	559 C°	872 C°	C°
						Mis

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
47.1	18.5	7.3	1.0	0.0	9.1

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.