

# DATA SHEET

20672104 'ESMALTE GRES O-10121 VERDE POLVO

18/11/2025 v1.4

## 1. PRODUCT IDENTIFICATION

Description	GREEN GLAZE. It belongs to high temperature glazes, with high rutile content. The result can be opaque matte. The final effect can be different depending on firing temperature, coat of glaze and kind of biscuit. The result will vary depending on the used body, temperature, cycle and atmosphere. Compound of frit: CAS N°. 65997-18-4.
Application	They can be applied by brush, spraying or dipping in single- and double-fired. For one firing it's advisable the addition of Monocol V. Temperature range 1240°C - 1360°C, recommended temperature 1260°C. It is advisable to test at extreme temperatures.

## 2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	ZnO	Cr <sub>2</sub> O <sub>3</sub>	CaF <sub>2</sub>	10-20		
Na <sub>2</sub> O 1-5	MnO	B <sub>2</sub> O <sub>3</sub>	Bi <sub>2</sub> O <sub>3</sub>		MEDIUM	0-0.5
K <sub>2</sub> O 1-5	CdO	V <sub>2</sub> O <sub>5</sub>	P <sub>2</sub> O <sub>5</sub>		LOI	1-5
MgO 0-0.5	CoO	MnO <sub>2</sub>	BeO			
CaO 0-0.5	NiO	SiO <sub>2</sub> 40-80	CeO <sub>2</sub>			
SrO	Al <sub>2</sub> O <sub>3</sub> 10-20	TiO <sub>2</sub> 1-5	CuO 1-5			
BaO	Fe <sub>2</sub> O <sub>3</sub> 0-0.5	ZrO <sub>2</sub> 0-0.5	Pr <sub>2</sub> O <sub>3</sub>			
PbO	Sb <sub>2</sub> O <sub>3</sub>	SnO <sub>2</sub>				

## 3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	Beige powder
Color(fired)	Green

## 4. COLORIMETRY

\* By Minolta ChromaControl (S)

L: 50.2	a: -5.2	b: 4.6
---------	---------	--------

## 5. DILATOMETRY

\* Data obtained with dilatometer BÄHR mod. DIL 801 L 10<sup>-7</sup> C<sup>-1</sup>

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T <sup>a</sup> Transformation	T <sup>a</sup> Softening	Melting point
57.5	56.9	60.6	66.8	568 C°	883 C°	>1150 C°

## 6. GRANULOMETRIC DISTRIBUTION (WET WAY)

\* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ	>25μ	>40μ	>70μ	>120μ	D50μ
49.9	15.2	5.1	0.7	0.0	10.0

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España  
+34961545588  
admon@prodesco.es  
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.