

# DATA SHEET

20770304 ESMALTE GRES O-10295 AZUL POLVO

20/11/2025 v1.2

## 1. PRODUCT IDENTIFICATION

Description BLUE GLAZE. It belongs to high temperature glazes. Compound of frit: CAS N°. 65997-18-4.

Application They can be applied by brush, spraying or dipping in single- and double-fired. For one firing it's advisable the addition of Monocol V. Temperature range 1240°C - 1340°C, recommended temperature 1260°C. It is advisable to test at extreme temperatures.

## 2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	1-5	ZnO	Cr <sub>2</sub> O <sub>3</sub>	CaF <sub>2</sub>		
Na <sub>2</sub> O	5-10	MnO	B <sub>2</sub> O <sub>3</sub>	Bi <sub>2</sub> O <sub>3</sub>	Co-Si	0-0.5
K <sub>2</sub> O	5-10	CdO	V <sub>2</sub> O <sub>5</sub>	P <sub>2</sub> O <sub>5</sub>	HfO <sub>2</sub>	0-0.5
MgO	0-0.5	CoO	MnO <sub>2</sub>	BeO	LOI	10-20
CaO	5-10	NiO	SiO <sub>2</sub>	CeO <sub>2</sub>		
SrO		Al <sub>2</sub> O <sub>3</sub>	40-80	TiO <sub>2</sub>	0-0.5	
BaO		Fe <sub>2</sub> O <sub>3</sub>	0-0.5	ZrO <sub>2</sub>	5-10	
PbO		Sb <sub>2</sub> O <sub>3</sub>		SnO <sub>2</sub>		
				Pr <sub>2</sub> O <sub>3</sub>		

## 3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	White powder	0,79
Color(fired)	Blue	355,55

## 4. COLORIMETRY

\* By Minolta ChromaControl (S)

L: 73.6	a: 0.9	b: -11.8
---------	--------	----------

## 5. DILATOMETRY

\* Data obtained with dilatometer BÄHR mod. DIL 801 L 10<sup>-7</sup> C<sup>-1</sup>

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T <sup>a</sup> Transformation	T <sup>a</sup> Softening	Melting point
105.2	107.8	132.7	229.3	503 C°	884 C°	>1000 C°

## 6. GRANULOMETRIC DISTRIBUTION (WET WAY)

\* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ	>25μ	>40μ	>70μ	>120μ	D50μ
49.8	17.2	5.6	0.5	0.1	10.0

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)



C/ Aviación 44, 46940 Manises, Valencia - España  
+34961545588  
admon@prodesco.es  
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.