

# DATA SHEET

20775207 'ESMALTE GRES O-7004 MATE ATOMIZADO

05/08/2025 v1.7

## 1. PRODUCT IDENTIFICATION

Description	It belongs to the reactive bases for high temperature with high zinc content. The result can be opaque matte or satin with white bluish tones depending on the interaction with the used body, stoneware or porcelain. The final effect can be different depending on firing temperature, coat of glaze and kind of biscuit. The result will vary depending on the used body, temperature, cycle and atmosphere. Compound of frit: CAS N°. 65997-18-4.
Application	It can be colored with natural metal oxides and some calcined colorants from the "P" Series compatible with zinc oxide. They can be applied by brush, spraying or dipping in single- and double-fired. For one firing it's advisable the addition of Monocol V. Temperature range 1220°C - 1340°C, recommended temperature 1260°C. It is advisable to test at extreme temperatures.

## 2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	1-5	ZnO	20-40	Cr <sub>2</sub> O <sub>3</sub>	CaF <sub>2</sub>		
Na <sub>2</sub> O		MnO		B <sub>2</sub> O <sub>3</sub>	Bi <sub>2</sub> O <sub>3</sub>	MEDIUM	0-0.5
K <sub>2</sub> O	1-5	CdO		V <sub>2</sub> O <sub>5</sub>	P <sub>2</sub> O <sub>5</sub>	LOI	1-5
MgO	0-0.5	CoO		MnO <sub>2</sub>	BeO		
CaO	5-10	NiO		SiO <sub>2</sub>	CeO <sub>2</sub>		
SrO		Al <sub>2</sub> O <sub>3</sub>	5-10	TiO <sub>2</sub>	CuO		
BaO		Fe <sub>2</sub> O <sub>3</sub>	0-0.5	ZrO <sub>2</sub>	Pr <sub>2</sub> O <sub>3</sub>		
PbO		Sb <sub>2</sub> O <sub>3</sub>		SnO <sub>2</sub>			

## 3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	White powder
Color(fired)	White

## 4. COLORIMETRY

\* By Minolta ChromaControl (S)

L: n.a	a: n.a	b: n.a
--------	--------	--------

## 5. DILATOMETRY

\* Data obtained with dilatometer BÄHR mod. DIL 801 L

10<sup>-7</sup> C<sup>-1</sup>

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T <sup>a</sup> Transformation	T <sup>a</sup> Softening	Melting point
54.	53.5	58.3	65.1	618 C°	791 C°	>1150 C°

## 6. GRANULOMETRIC DISTRIBUTION (WET WAY)

\* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ	>25μ	>40μ	>70μ	>120μ	D50μ
44.0	20.0	8.7	1.2	0.0	7.5

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)



C/ Aviación 44, 46940 Manises, Valencia - España  
+34961545588  
admon@prodesco.es  
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.