1. PRODUCT IDENTIFICATION

Description

It belongs to the reactive bases for high temperature with high zinc content. The final effect can be different depending on firing temperature, coat of glaze and kind of biscuit. The result will vary depending on the used body, temperature, cycle and atmosphere. Compound of frit: CAS N°. 65997-18-4.

Application

It can be colored with natural metal oxides and some calcined colorants from the "P" Series compatible with zinc oxide. They can be applied by brush, spraying or dipping in single- and double-fired. For one firing it's advisable the addition of Monocol V. Temperature range 1200°C - 1340°C, recommended temperature 1260°C. It is advisable to test at extreme temperatures.

2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O Na ₂ O	1-5	ZnO 1 MnO	0-20	Cr ₂ O ₃ B ₂ O ₃	CaF₂ Bi₂O₃	MEDIUM	0-0.5
K_2O	1-5	CdO		V ₂ O ₅	P ₂ O ₅	LOI	5-10
MgO	0-0.5	CoO		MnO_2	BeO		
CaO	5-10	NiO		SiO ₂ 40-80	CeO ₂		
SrO		Al_2O_3 1	0-20	TiO ₂ 0-0.5	CuO		
BaO		Fe ₂ O ₃ C)-0.5	ZrO_2	Pr ₂ O ₃		
PbO		Sb_2O_3		SnO_2			

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect White powder Color(fired) Transparent

4. COLORIMETRY * By Minolta ChromaControl (S)

L: n.a a: n.a b: n.a

5. DILATOMETRY * Data obtained with dilatometer BÄHR mod. DIL 801 L

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
55.6	55.4	61.6	69.5	638 C°	874 C°	>1150 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) * Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
50.8	20.8	8.6	1.1	0.0	10.3

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

