

DATA SHEET

20778304 'ESMALTE GRES O-10583 AMARILLO POLV

08/01/2026 v1.3

1. PRODUCT IDENTIFICATION

Description Yellow glaze (contains Zn)
It belongs to high temperature glazes.

Application The glaze can be coloured natural and synthetic oxides. It admits either once firing. It can be applied over: porcelain, stoneware and over any of their varieties. The range for temperatures varies from 1200 to 1320°C.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	ZnO	5-10	Cr ₂ O ₃	CaF ₂	Cd(S,Se) en ZrSiO ₄	10-20
Na ₂ O	1-5	MnO	B ₂ O ₃	Bi ₂ O ₃	LOI	5-10
K ₂ O	1-5	CdO	V ₂ O ₅	P ₂ O ₅	Pig.Ing	0-0.5
MgO	0-0.5	CoO	MnO ₂	BeO		
CaO	5-10	NiO	SiO ₂	40-80	CeO ₂	
SrO		Al ₂ O ₃	5-10	TiO ₂	0-0.5	
BaO		Fe ₂ O ₃	0-0.5	ZrO ₂		
PbO		Sb ₂ O ₃		SnO ₂		

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Yellow powder
Color(fired) Yellow

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: 76.18 a: 1.46 b: 82.15

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10^{-7} C^{-1}

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
74.5	74.9	87.0	112.6	521 C°	884 C°	>1100 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
49.5	21.3	9.0	1.2	0.0	9.8

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Contains inclusion cadmium pigment. To certify their food use, the final pieces must be submitted to lead migration test by an accredited laboratory.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.