

# DATA SHEET

22204607 ESMALTE 5585 BLANCO NAZARI ATOMIZA

05/02/2025 v1.4

## 1. PRODUCT IDENTIFICATION

Description	White and Glossy lead Glaze suitable for use on white and red body, pottery and colored body. It can be used on standard bodies because its low TEC. Compound of frit: CAS N°. 65997-18-4.
Application	It can be applied :dipping, spraying, slip-trail for "CUERDA SECA" technique and any mechanical method of application. It can be coloured with our Pigments "P" Series, keeping in mind it contains Zr . It is recommended to make previous test for colouring with natural oxides. "CD Series"and "Decor Series" of On- glaze colours can be used for decoration. The recommended temperature varies from 960°-1020°C.

## 2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	1-5	ZnO		Cr <sub>2</sub> O <sub>3</sub>		CaF <sub>2</sub>	
Na <sub>2</sub> O		MnO		B <sub>2</sub> O <sub>3</sub>	5-10	Bi <sub>2</sub> O <sub>3</sub>	LOI 1-5
K <sub>2</sub> O	0.5-1	CdO		V <sub>2</sub> O <sub>5</sub>		P <sub>2</sub> O <sub>5</sub>	
MgO	0-0.5	CoO		MnO <sub>2</sub>		BeO	
CaO	1-5	NiO		SiO <sub>2</sub>	40-80	CeO <sub>2</sub>	
SrO		Al <sub>2</sub> O <sub>3</sub>	5-10	TiO <sub>2</sub>	0-0.5	CuO	
BaO		Fe <sub>2</sub> O <sub>3</sub>	0-0.5	ZrO <sub>2</sub>	10-20	Pr <sub>2</sub> O <sub>3</sub>	
PbO	1-5	Sb <sub>2</sub> O <sub>3</sub>		SnO <sub>2</sub>			

## 3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	White powder
Color(fired)	White Bright

## 4. COLORIMETRY

\* By Minolta ChromaControl (S)

L: n.a	a: n.a	b: n.a
--------	--------	--------

5. DILATOMETRY				* Data obtained with dilatometer BÄHR mod. DIL 801 L			10 <sup>-7</sup> C <sup>-1</sup>
(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T <sup>a</sup> Transformation	T <sup>a</sup> Softening	Melting point	
65.0	63.6	63.9	74.2	608 C°	692 C°	>900 C°	

6. GRANULOMETRIC DISTRIBUTION (WET WAY)					* Data obtained by Malvern Instruments (Master Sizer 2000)
>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
66.6	35.0	16.5	2.7	0.0	17.0

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Compound of lead frit. To certify their food use, the final pieces must be submitted to lead migration test by an accredited laboratory.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)



C/ Aviación 44, 46940 Manises, Valencia - España  
+34961545588  
admon@prodesco.es  
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.