

DATA SHEET

22288407 ESMALTE 5880 BLANCO MATE S/Pb. ATOM

17/02/2025 v1.4

1. PRODUCT IDENTIFICATION

Description	White Matt Glaze suitable for use on white and red rody, pottery and colored body. Compound of frit: CAS N°. 65997-18-4.
Application	It can be applied :dipping, spraying, any mechanical method of application.It can be coloured with our Pigments "P" Series, keeping in mind it contains Zr and Zn. It is recommended to make previous test for colouring with natural oxides and firing cycles over 1080 °C. "CD Series" of On-glaze colours can be used for decoration. The recommended temperature varies from 980°C-1080°C.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	5-10	ZnO	10-20	Cr ₂ O ₃		CaF ₂	
Na ₂ O		MnO		B ₂ O ₃	5-10	Bi ₂ O ₃	HfO ₂ 0-0.5
K ₂ O	0-0.5	CdO		V ₂ O ₅		P ₂ O ₅	MEDIUM 0-0.5
MgO	0-0.5	CoO		MnO ₂		BeO	LOI 1-5
CaO	5-10	NiO		SiO ₂	40-80	CeO ₂	
SrO		Al ₂ O ₃	5-10	TiO ₂	0-0.5	CuO	
BaO	1-5	Fe ₂ O ₃	0-0.5	ZrO ₂	5-10	Pr ₂ O ₃	
PbO		Sb ₂ O ₃		SnO ₂			

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	White powder
Color(fired)	White matt

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: n.a	a: n.a	b: n.a
--------	--------	--------

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10⁻⁷ C⁻¹

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	Tª Transformation	Tª Softening	Melting point
61.5	62.2	72.5	160	525 C°	864 C°	>980 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
58.9	27.6	12.6	2.3	0	13.3

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)



C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.