Description

TRANSPARENT GLAZE. This is a very bright glaze recommended for ceramicware. Compound of frit: CAS No. 65997-18-4.

Application

It can be applied: dipping, spraying, any mechanical application method. Glaze suitable for use on white, red and colored body. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes, which will depend on the body.

## 2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O		ZnO	$Cr_2O_3$	CaF <sub>2</sub>
Na <sub>2</sub> O	5-10	MnO	B <sub>2</sub> O <sub>3</sub> 10-20	$Bi_2O_3$
$K_2O$	1-5	CdO	$V_2O_5$	P <sub>2</sub> O <sub>5</sub>
MgO	0-0.5	CoO	$MnO_2$	BeO
CaO	5-10	NiO	SiO <sub>2</sub> 40-80	CeO <sub>2</sub>
SrO		Al <sub>2</sub> O <sub>3</sub> <b>5-10</b>	TiO <sub>2</sub> <b>0-0.5</b>	CuO
BaO	1-5	Fe <sub>2</sub> O <sub>3</sub> <b>0-0.5</b>	$ZrO_2$	Pr <sub>2</sub> O <sub>3</sub>
PbO		$Sb_2O_3$	$SnO_2$	

## **3 PHYSICAL-CHEMICAL PROPERTIES**

Aspect White powder

Color(fired) White

4. COLORIMETRY \* By Minolta ChromaControl (S)

L: **86.4** a: **-1.6** b: **3.6** 

**5. DILATOMETRY** \* Data obtained with dilatometer BÄHR mod. DIL 801 L 10 <sup>-7</sup> C<sup>-1</sup>

(25-300)C° (50-300)C° (300-500)C° (500-600)C° T<sup>a</sup> Transformation T<sup>a</sup> Softening Melting point 71.03 70.86 74.66 112.76 582 C° 706 C° >850 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) \* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ >25μ >40μ >70μ >120μ D50μ 57.8 22.71 9.35 0.98 0 12.72

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

