

DATA SHEET

41130704 ESM. EOSP-07 OPACO V.CROMO POLVO

22/10/2024 v1.3

1. PRODUCT IDENTIFICATION

Description BRIGHT OPAQUE GREEN CHROMEGLAZE. It belongs to the "EOSP" series, opaque glazes, formulated without lead in their composition. Compound of frit: CAS N°. 65997-18-4.

Application The glaze can be applied by dipping, brush, screen printing or spray and can be used for decoration of white body or red clay. This collection of glazes is suitable for use in single firing or double firing. When using these products in a single-firing process, it is advisable to add a 5% solution of Monocol V. The firing recommended temperature varies from 980 °C to 1080°C. However, they can be fired at higher temperatures to obtain the same or different finishes, depending on the type of clay used.

2. CHEMICAL COMPOSITION Los óxidos metálicos con concentraciones inferiores a 0,05% no han sido determinados.

Li ₂ O	ZnO	1-5	Cr ₂ O ₃	CaF ₂			
Na ₂ O	1-5	MnO	B ₂ O ₃	10-20	Bi ₂ O ₃	Co-Cr-Al	1-5
K ₂ O	1-5	CdO	V ₂ O ₅		P ₂ O ₅	LOI	0.5-1
MgO	0-0.5	CoO	MnO ₂		BeO	Zr-Pr-Si	0-0.5
CaO	5-10	NiO	SiO ₂	40-80	CeO ₂		
SrO		Al ₂ O ₃	TiO ₂	0-0.5	CuO		
BaO	0.5-1	Fe ₂ O ₃	ZrO ₂	5-10	Pr ₂ O ₃		
PbO		Sb ₂ O ₃	SnO ₂				

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Green powder
Color(fired) Bright green chrome

4. COLORIMETRY * By Minolta ChromaControl (S)

L: 50.8 a: -16.2 b: 13.5

5. DILATOMETRY * Data obtained with dilatometer BÄHR mod. DIL 801 L 10⁻⁷ C⁻¹

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
59.95	59.43	63.04	99.04	592 C°	668 C°	>850 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) * Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
60	30	13	2	0	15.5

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

Los datos incluidos en esta ficha han sido obtenidos en las condiciones específicas del proceso de control de calidad de PRODESCO S.L. y son sólo a título informativo, no suponiendo relación contractual alguna..