Description

TRANSPARENT TURQUOISE GLAZE. This is a very bright glaze recommended for ceramicware. Compound of frit: CAS No. 65997-18-4.

Application

It can be applied: dipping, spraying, any mechanical application method. Glaze suitable for use on white, red and colored body. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes, which will depend on the body.

## 2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O	ZnO	$Cr_2O_3$	CaF <sub>2</sub>	
Na <sub>2</sub> O	MnO	$B_2O_3$	$Bi_2O_3$	
$K_2O$	CdO	$V_2O_5$	P <sub>2</sub> O <sub>5</sub>	
MgO	CoO	$MnO_2$	BeO	
CaO	NiO	SiO <sub>2</sub>	CeO <sub>2</sub>	
SrO	$Al_2O_3$	TiO <sub>2</sub>	CuO	
BaO	Fe <sub>2</sub> O <sub>3</sub>	$ZrO_2$	Pr <sub>2</sub> O <sub>3</sub>	
PbO	$Sb_2O_3$	$SnO_2$		

## **3 PHYSICAL-CHEMICAL PROPERTIES**

Aspect	Blue powder
Color(fired)	Turquoise

### 4. COLORIMETRY

\* By Minolta ChromaControl (S)

•	51.8		
	31.0		

a: -10.3 b: -30.5

#### 10 <sup>-7</sup> C<sup>-1</sup> 5. DILATOMETRY \* Data obtained with dilatometer BÄHR mod. DIL 801 L

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T <sup>a</sup> Transformation	T <sup>a</sup> Softening	Melting point
71.03	70.86	74.66	112.76	582 C°	706 C°	>850 C°

# 6. GRANULOMETRIC DISTRIBUTION (WET WAY)

\* Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
57.8	22.71	9.35	0.98	0	12.72

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

