

DATA SHEET

41142304 ESM. ETSP-25 TRANSP.COÑAC POLVO

09/04/2025 v1.1

1. PRODUCT IDENTIFICATION

Description TRANSPARENT COGNAC GLAZE. This is a transparent, coloured and very bright glaze formulated without lead in its composition. Compound of frit: CAS N°. 65997-18-4.

Application It can be applied: dipping, spraying, any mechanical application method. Glaze suitable for use on white clay. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	ZnO	0.5-1	Cr ₂ O ₃	CaF ₂				
Na ₂ O	1-5	MnO	0-0.5	B ₂ O ₃	5-10	Bi ₂ O ₃	MEDIUM	0-0.5
K ₂ O	1-5	CdO		V ₂ O ₅		P ₂ O ₅	LOI	1-5
MgO	1-5	CoO		MnO ₂	1-5	BeO		
CaO	1-5	NiO		SiO ₂	20-40	CeO ₂		
SrO		Al ₂ O ₃	5-10	TiO ₂	0-0.5	CuO		
BaO	1-5	Fe ₂ O ₃	1-5	ZrO ₂		Pr ₂ O ₃		
PbO		Sb ₂ O ₃		SnO ₂				

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Grey powder
Color(fired) Cognac

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: 31.5 a: 13.4 b: 10.0

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10^{-7} C^{-1}

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
71.03	70.86	74.66	112.76	582 C°	706 C°	>850 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ	>25µ	>40µ	>70µ	>120µ	D50µ
57.8	22.71	9.35	0.98	0	12.72

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.