

DATA SHEET

41142404 'ESM. ETSP-26 TR. VERDE COBRE POLVO

22/11/2024 v1.3

1. PRODUCT IDENTIFICATION

Description TRANSPARENT COPPER GREEN GLAZE. This is a very bright glaze recommended for ceramicware.
Compound of frit: CAS N°. 65997-18-4.

Application It can be applied: dipping, spraying, any mechanical application method. Glaze suitable for use on white, red and colored body. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes, which will depend on the body.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O		ZnO	0-0.5	Cr ₂ O ₃		CaF ₂	
Na ₂ O	0-0.5	MnO		B ₂ O ₃	5-10	Bi ₂ O ₃	MEDIUM 0-0.5
K ₂ O	1-5	CdO		V ₂ O ₅		P ₂ O ₅	LOI 1-5
MgO	0.5-1	CoO		MnO ₂		BeO	Pig.Ing 0-0.5
CaO	0-0.5	NiO		SiO ₂	10-20	CeO ₂	
SrO	1-5	Al ₂ O ₃	5-10	TiO ₂	0-0.5	CuO	5-10
BaO	0-0.5	Fe ₂ O ₃	0.5-1	ZrO ₂		Pr ₂ O ₃	
PbO		Sb ₂ O ₃		SnO ₂			

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Green powder
Color(fired) Copper green

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: 40.6 a: -6.5 b: -0.5

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10⁻⁷ C⁻¹

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
71.03	70.86	74.66	112.76	582 C°	706 C°	>850 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ	>25μ	>40μ	>70μ	>120μ	D50μ
57.8	22.71	9.35	0.98	0	12.72

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)



C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.