

DATA SHEET

41151604 ESM. EMSP-16 GRIS MATE POLVO

26/02/2025 v1.4

1. PRODUCT IDENTIFICATION

Description	MAT GREY GLAZE.It belongs to the "EMSP" series recommended for ceramicware. Compound of frit: CAS N°. 65997-18-4.
Application	The glazes can be decorated by the coulors of serie CD for application over white or red bodies. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes.

2. CHEMICAL COMPOSITION

Metal oxides with concentrations less than 0.05% have not been determined.

Li ₂ O	5-10	ZnO	10-20	Cr ₂ O ₃	CaF ₂	Co-Fe-Cr	0-0.5
Na ₂ O		MnO		B ₂ O ₃	Bi ₂ O ₃	Cr-Fe-Zn-Co	0-0.5
K ₂ O	0-0.5	CdO		V ₂ O ₅	P ₂ O ₅	HfO ₂	0-0.5
MgO	0-0.5	CoO		MnO ₂	BeO	MEDIUM	0-0.5
CaO	5-10	NiO		SiO ₂	CeO ₂	LOI	1-5
SrO		Al ₂ O ₃	5-10	TiO ₂	CuO		
BaO	1-5	Fe ₂ O ₃	0-0.5	ZrO ₂	Pr ₂ O ₃		
PbO		Sb ₂ O ₃		SnO ₂			

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect	Grey powder
Color(fired)	Grey

4. COLORIMETRY

* By Minolta ChromaControl (S)

L: 58.32	a: 1.42	b: 2.15
----------	---------	---------

5. DILATOMETRY

* Data obtained with dilatometer BÄHR mod. DIL 801 L 10⁻⁷ C⁻¹

(25-300)C°	(50-300)C°	(300-500)C°	(500-600)C°	T ^a Transformation	T ^a Softening	Melting point
69.8	68.5	80.6	183.5	561 C°	650 C°	>875 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY)

* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ	>25μ	>40μ	>70μ	>120μ	D50μ
65.7	34.1	17.1	3.9	0	16.4

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

 PRODESCO S.L.

C/ Aviación 44, 46940 Manises, Valencia - España
+34961545588
admon@prodesco.es
www.prodesco.es

The provide data have been obtained under the specific conditions of the quality control process of PRODESCO S.L. being for informational purposes, not assuming any contractual relationship.