## 1. PRODUCT IDENTIFICATION

Description

MAT DRAK GREY GLAZE.It belongs to the "EMSP" series recommended for ceramicware. Compound of frit: CAS N°. 65997-18-4.

Application

The glazes can be decorated by the coulors of serie CD for application over white or red bodies. The firing recommended temperature varies from 980 °C to 1080°C. They can be used at higher temperatures obtaining the same or even other finishes.

## 2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined.

Li <sub>2</sub> O		ZnO	10-20	$Cr_2O_3$		CaF <sub>2</sub>		
Na <sub>2</sub> O	5-10	MnO		$B_2O_3$	5-10	$Bi_2O_3$	Co-Fe-Cr	1-5
$K_2O$	0-0.5	CdO		$V_2O_5$		$P_2O_5$	Hf02	0-0.5
MgO	0-0.5	CoO		$MnO_2$		BeO	MEDIUM	0-0.5
CaO	5-10	NiO		$SiO_2$	40-80	CeO <sub>2</sub>	INIEDIOM	0-0.5
SrO		$Al_2O_3$	5-10	TiO <sub>2</sub>	0-0.5	CuO	LOI	1-5
BaO	1-5	$Fe_2O_3$	0-0.5	$ZrO_2$	5-10	$Pr_2O_3$		
PbO		$Sb_2O_3$		$SnO_2$				

## **3 PHYSICAL-CHEMICAL PROPERTIES**

Aspect Grey powder Color(fired) Dark grey

4. COLORIMETRY \* By Minolta ChromaControl (S)

L: **48.14** a: **-0.4** b: **-3.57** 

**5. DILATOMETRY** \* Data obtained with dilatometer BÄHR mod. DIL 801 L 10 <sup>-7</sup> C<sup>-1</sup>

(25-300)C° (50-300)C° (300-500)C° (500-600)C° T<sup>a</sup> Transformation T<sup>a</sup> Softening Melting point 69.8 68.5 80.6 183.5 561 C° 650 C° >875 C°

6. GRANULOMETRIC DISTRIBUTION (WET WAY) \* Data obtained by Malvern Instruments (Master Sizer 2000)

>10μ >25μ >40μ >70μ >120μ D50μ 65.7 34.1 17.1 3.9 0 16.4

## 7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Formulated without lead and cadmium.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

