Co

Mis

1. PRODUCT IDENTIFICATION

Description

Inorganic pigment. Inclusion pigment, Cd(S,Se) en ZrSiO4. Maximun operating temperature 1250°C.

Application

This series of pure pigments can be used both for coloring glazes, as for onglaze/underglaze decoration. In the first case, the intensity of the color will depend on the components of the glaze, as well as the cycle and the firing temperature. In the second case, the pigment should be mixed with a flux: lead flux Decor-flux-5 or Flux No. 50 and lead-free in composition flux: Flux 20 or Glaze F-15. The percentages of addition range 30-60%.

2. CHEMICAL COMPOSITION Metal oxides with concentrations less than 0.05% have not been determined

3 PHYSICAL-CHEMICAL PROPERTIES

Aspect Red

Color(fired) Red powder.

4. COLORIMETRY * By Minolta ChromaControl (S)

L: 41.52 a: 38.23 b: 19.19

5. DILATOMETRY * Data obtained with dilatometer BÄHR mod. DIL 801 L

(25-300)C° (50-300)C° (300-500)C° (500-600)C° Ta Transformation Ta Softening Melting point

Co Co

6. GRANULOMETRIC DISTRIBUTION (WET WAY) * Data obtained by Malvern Instruments (Master Sizer 2000)

>10µ >25µ >40µ >70µ >120µ D50µ

7. RECOMMENDATIONS ON GLAZED OBJECTS INTENDED FOR CULINARY USE

Contains inclusion cadmium pigment. To certify their food use, the final pieces must be submitted to lead migration test by an accredited laboratory.

Notes: n.a (not applicable), n.d (no information available), p.n (negative tests)

