



REFRACTORY CEMENT MP-140

Air set mortar for refractory joints Mortar for joining refractory bricks

COMPOSITION: Silica-aluminum Basis $\text{SiO}_2 + \text{Al}_2\text{O}_3 = 96\%$.

Fe_2O_3 0,3 %

CaO 0,4 %

APPLICATION: Ready for use. Application with spatula. (See sheet of use)

PHYSICAL PROPERTIES

Classification Temperature 1400 °C ISO 1927-1

Open Porosity (Dry 110°C) 28,00 % ISO 1927-6

REMARKS

For bricks joining up to 45% of Al_2O_3 .

Packaging plastic box 5 kg and 25 kg.

Storage limit well covered 1 year.

Do not hesitate to contact our Technical Department for any questions or clarifications.

Shop

Balmes, 29
46940 Manises Valencia (ESPAÑA)

(+34) 96 154 88 21
latienda@prodesco.es
<http://prodesco.es>

Company

Aviación, 44
46940 Manises Valencia (ESPAÑA)

(+34) 96 154 55 88
admon@prodesco.es
<http://prodesco.es>