

This is a collection of pottery glazes, with an excellent shine and surface quality. They are formulated lead and cadmium free compounds. To certify their food use, the final pieces must be submitted to lead migration test by an accredited laboratory.

Although they can be applied on all types of red and white clay bodies and also chamotte-based clay bodies, the specific characteristics of each reference means that one may be more suitable to obtain the best result, according to the piece to which they're applied.

For red clay bodies, including those for direct firing, that are once-fire, the addition of MONOCOL V (5%) is recommended.

They can be fired in cycles of traditional firing and rapid firing, allowing for a wide range of temperatures, between 930° - 1020 °C.

REFERENCES AND RECOMMENDED TEMPERATURES:

XP-3043 HONEY(930-980°C)

C/4 HONEY (930-980°C)

XP-3128 CINNAMON (930-980°C)

XP-3085 BLUE (930-980°C)

XP-3048 GREEN (960-1050°C)

XP-3025 GREEN (960-1050°C)

XP-3072 BLACK (960-1050°C)

5600 COGNAC (980-1050°C)

If needed, do not hesitate to contact our Technical Department for any queries or clarifications.

Shop

Balmes, 29
46940 Manises Valencia (Spain)

(+34) 96 154 88 21
latienda@prodesco.es
<http://prodesco.es>

Factory

Aviación, 44
46940 Manises Valencia (ESPAÑA)

(+34) 96 154 55 88
admon@prodesco.es
<http://prodesco.es>